

## TECAPEI GF 30

Chemical Designation :  
 DIN-Abbreviation:  
 Colours, fillers:

Polyetherimide  
 PEI GF 30  
 natural, 30 % glass fibres

---

### Main features

- | high thermal and mechanical capacity
- | inherently flame retardant (UL94 V-O)
- | high dimensional stability
- | high heat deflection temperature
- | good creep resistance
- | good electrical insulation
- | good radiation resistance
- | continuous service temperature up to 170°C

---

### Preferred Fields

- | Semiconductor technology
- | automotive engineering
- | transport and conveyor technology
- | mechanical engineering
- | vacuum technology
- | pumps and instrument manufacture

---

### Applications

---

### Properties

#### Mechanical

|                                  | dry / moist | standard           |
|----------------------------------|-------------|--------------------|
| Tensile strength at yield        |             | MPa                |
| Elongation at yield              |             | %                  |
| Tensile strength at break        | 165         | MPa DIN EN ISO 527 |
| Elongation at break              | 2           | % DIN EN ISO 527   |
| Modulus of elasticity in tension | 9500        | MPa                |

|   |      |                   |                              |
|---|------|-------------------|------------------------------|
| Modulus of elasticity after flexural test   | 9000 | MPa               | DIN EN ISO 178               |
| Hardness  | 165  |                   | DIN 53 456 (Kugeldruckhärte) |
| Impact strength 23° C (Charpy)  | 40   | KJ/m <sup>2</sup> | DIN EN ISO 179 (Charpy)      |
| Creep rupture strength after 1000 h with static load  |      | MPa               |                              |
| Time yield limit for 1% elongation after 1000 h   |      | MPa               |                              |
| Co-efficient of friction<br>p = 0,05 N/mm <sup>2</sup> v=0,6 m/s<br>on steel, hardened and ground |      |                   |                              |

Wear µm/km  
p = 0,05 N/mm<sup>2</sup>v=0,6 m/s  
on steel, hardened and ground

#### Thermal

|   | dry / moist |                     | standard                          |
|---|-------------|---------------------|-----------------------------------|
| Crystalline melting point                     |             | °C                  |                                   |
| Glass transition temperature                  | 217         | °C                  | DIN 53 765                        |
| Heat distortion temperature<br>HDT, Method A  | 210         | °C                  | ISO-R 75 Verfahren A (DIN 53 461) |
| Heat distortion temperature<br>HDT, Method B  | 215         | °C                  | ISO-R 75 Verfahren B (DIN 53 461) |
| Max. service temperature                      |             |                     |                                   |
| short term                                    | 200         | °C                  |                                   |
| long term                                     | 170         | °C                  |                                   |
| Thermal conductivity (23° C)                  | 0,23        | W/(K·m)             |                                   |
| Specific heat (23° C)                         |             | J/g.K               |                                   |
| Coefficient of thermal expansion<br>(23–55°C) | 2           | 10 <sup>-5</sup> /K | DIN 53 752                        |

## Properties

---

| <b>Electrical</b>                   | <b>dry / moist</b>     | <b>standard</b>                      |
|-------------------------------------|------------------------|--------------------------------------|
| Dielectric constant ( $10^6$ Hz)    | 3,7                    | DIN 53 483, IEC-250                  |
| Dielectric loss factor ( $10^6$ Hz) | 0,007                  | DIN 53 483, IEC-250                  |
| Specific volume resistance          | $10^{15}$ $\Omega$ *cm | DIN IEC 60093                        |
| Surface resistance                  | $10^{15}$ $\Omega$     | DIN IEC 60093                        |
| Dielectric strength                 | 30 kV/mm               | DIN 53 481, IEC-243, VDE 0303 Teil 2 |
| Resistance to tracking              |                        |                                      |

---

| <b>Miscellaneous</b>                | <b>dry / moist</b>     | <b>standard</b> |
|-------------------------------------|------------------------|-----------------|
| Density                             | 1,51 g/cm <sup>3</sup> | DIN 53 479      |
| Moisture absorption (23°C/50RH)     | 0,5 %                  | DIN EN ISO 62   |
| Water absorption to equilibrium     | 0,9 %                  | DIN EN ISO 62   |
| Flammability acc. to UL standard 94 | V0                     |                 |

(1) Testing of semi-finished products

The above information corresponds with our current knowledge and indicates our products and possible applications. We cannot give a legally binding guarantee of chemical resistance, of certain properties and the suitability of our products and their applications. Our products are not destined for use in medical and dental implants. Existing commercial patents must be observed. Unless otherwise stated, these values represent averages taken from injection moulding samples, dry as moulded. We reserve the right to make technical alterations.

---