

CHEMFAB®

ANTI-STATIC, PTFE-COATED GLASS

CHEMFAB® Anti-static Series is a high quality PTFE-coated glass fabric that can be used for release sheets, belting, or other applications requiring the dissipation of static electricity.

Typical Properties

| Product Number | CF5-03 | CF5-05 | CF5-06 | CF5-06TT | CF5-10 | CF5-10TT | CF5-14 |
|---|---------------------|---------------------|---------------------|---------------------|---------------------|---------------------|---------------------|
| Standard Width* (in.) | 40 | 40 | 40 | 40 | 40 | 40 | 40 |
| Weight Nominal (oz./yd ²) | 4.3 | 7.9 | 9.3 | 7.9 | 15.5 | 15.5 | 21.0 |
| Thickness Nominal (in.) | 0.003 | 0.005 | 0.0055 | 0.005 | 0.010 | 0.010 | .0014 |
| Breaking Strength (lbs./in.) | | | | | | | |
| Warp | 70 | 120 | 125 | 120 | 200 | 200 | 350 |
| Fill | 50 | 100 | 160 | 100 | 150 | 150 | 250 |
| Trapezoidal Tear (lbs.) | | | | | | | |
| Warp | 1.5 | 3.0 | 3.0 | 3.0 | 8.0 | 8.0 | 10.0 |
| Fill | 1.0 | 3.0 | 3.5 | 3.0 | 6.0 | 6.0 | 8.0 |
| Surface Resistivity (ohms/sq.) | <1 x10 ⁶ | <1 x10 ⁶ | <1 x10 ⁶ | <1 x10 ⁶ | <1 x10 ⁶ | <1 x10 ⁶ | <1 x10 ⁶ |

*Other widths may be available. Please consult the factory.

The data listed herein fall within the normal range of product properties for the products described, but they should not be used to establish specification limits nor used alone as the basis of design. Saint-Gobain assumes no obligation or liability for any advice furnished by it or for results obtained with respect to these products. All such advice is provided gratis and Buyer assumes sole responsibility for results obtained in reliance thereon. Saint-Gobain warrants that the material itself does not infringe any United States patent, but no license is implied nor is any further warranty made.

Saint-Gobain Performance Plastics Corporation
150 Gaylord Street
Elk Grove Village, IL 60007
Customer Service: (800) 323-6677
Tel: (847) 364-0384
Fax: (888) 394-1156

www.fff.saint-gobain.com

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.

CHEMFAB® is a registered trademark.

©2004 Saint-Gobain Performance Plastics Corporation
AFF-1155-PDF-0104-SGCS