

PMMA - Cast Acrylic Sheets - Delivery programme

White and opal Colours

RXacryl

White and opals

Colour	Light trasmission	2030 x 3050 Thickness mm	2020 x 3050 Thickness mm
2005	84%	3	
2009	70%	3 - 4 - 5	
2002	48%	3 - 4 - 5	
2008	40%	3 - 4 - 5	6 - 8
2007	34%	3 - 4 - 5	
2006	32%	3 - 4 - 5	6 - 8
2000	29%	3 - 4 - 5	
2001	25%	3 - 4 - 5	
4000	10%	3 - 4 - 5	6 - 8 - 10
4013	4%	3 - 4 - 5	6

Viewside

For colours and opals, white protection is identifying the side to be used.

Colour intensity

The colour intensity remains constant up to 10 mm. thickness.

ISO 7823-1 Thickness tolerances

ISO 7823-1 following thickness tolerances are accepted:

+/- (0,4 + 0,1 s) where **s** is the nominal thickness in mm.