



Material Data Sheet, October 2005

TECASON P MT sw

Chemical Designation :

Polyphenylsulfone

DIN-Abbreviation:

PPSU

Colours, fillers:

schwarz

Main features

- | high thermal and mechanical capacity
- | inherently flame retardant (UL94 V-O)
- | high hardness and rigidity
- | high heat deflection temperature
- | very resistant to gamma radiation
- | high impact strength and notched impact strength
- | good chemical resistance
- | good hydrolysis resistance
- | food contact notification
- | good weldability

Preferred Fields

- | medical technology
- | chemical engineering
- | food technology
- | electrical engineering
- | vacuum technology
- | pumps and instrument manufacture
- | precision engineering
- | automotive engineering

Applications

surgical instruments, sterilization tanks, instrument handles, appliances, sensor housings, valve bodies, seals

Properties

Mechanical

Tensile strength at yield

dry / moist

70

standard

MPa

DIN EN ISO 527

Elongation at yield

%

Tensile strength at break		MPa	
Elongation at break	> 50	%	DIN EN ISO 527
Modulus of elasticity in tension	2350	MPa	
Modulus of elasticity after flexural test	2600	MPa	DIN EN ISO 178
Hardness	31		DIN 53 456 (Kugeldruckhärte)
Impact strength 23° C (Charpy)	n.b.	KJ/m ²	DIN EN ISO 179 (Charpy)
Creep rupture strength after 1000 h with static load		MPa	
Time yield limit for 1% elongation after 1000 h		MPa	
Co-efficient of friction $p = 0,05 \text{ N/mm}^2 v=0,6 \text{ m/s}$ on steel, hardened and ground			
Wear $p = 0,05 \text{ N/mm}^2 v=0,6 \text{ m/s}$ on steel, hardened and ground		µm/km	

Thermal	dry / moist	standard
Crystalline melting point		°C
Glass transition temperature	220	°C
Heat distortion temperature HDT, Method A	207	°C
Heat distortion temperature HDT, Method B	214	°C
Max. service temperature		ISO-R 75 Verfahren B (DIN 53 461)
short term	190	°C
long term	170	°C
Thermal conductivity (23° C)	0,35	W/(K.m)
Specific heat (23° C)		J/g.K
Coefficient of thermal expansion (23–55°C)	5,6	10 ⁻⁵ 1/K
		DIN 53 752

Properties

Electrical

	dry / moist	standard
Dielectric constant (10^6 Hz)	3,45	DIN 53 483, IEC-250
Dielectric loss factor (10^6 Hz)		DIN 53 483, IEC-250
Specific volume resistance	10^{15}	$\Omega \cdot \text{cm}$
Surface resistance	10^{15}	Ω
Dielectric strength	15	kV/mm
Resistance to tracking		DIN 53 481, IEC-243, VDE 0303 Teil 2
		DIN 53 480, VDE 0303 Teil 1

Miscellaneous

	dry / moist	standard
Density	1,29	g/cm^3
Moisture absorption (23°C/50RH)	0,37	%
Water absorption to equilibrium	1,1	%
Flammability acc. to UL standard 94	V0	DIN 53 495

(1) Testing of semi-finished products

The above information corresponds with our current knowledge and indicates our products and possible applications. We cannot give a legally binding guarantee of chemical resistance, of certain properties and the suitability of our products and their applications. Our products are not destined for use in medical and dental implants. Existing commercial patents must be observed. Unless otherwise stated, these values represent averages taken from injection moulding samples, dry as moulded. We reserve the right to make technical alterations.